



STOPGAP 800 WEARCOAT

Self-levelling Wearing Surface

Screed classification : CT-C40-F10-AR0.5 to EN 13813:2002



Scan to view the product demonstration video



PRODUCT DATA

INTRODUCTION

STOPGAP 800 is a self-levelling commercial and industrial grade floor compound used for upgrading and renovating new and existing internal floors in light to heavy-duty applications where floorcoverings are not required to be installed. It is suitable for use in areas such as storerooms, post rooms, workshops, corridors, warehouses etc. STOPGAP 800 is grey in colour.

STOPGAP 800 is dimensionally stable and is supplied as a pre-blended dry powder, which is designed for application between 5-15mm. It is protein-free which allows it to be used in biologically sensitive areas.

STOPGAP 800 is for application over a wide range of subfloor types including sand / cement screed, concrete, granolithic, terrazzo, epoxy and polyurethane resins and STOPGAP waterproof surface membranes.

In areas where water or other fluids may come into direct contact with the cured material, the surface must be sealed with STOPGAP SEAL. This also helps to protect the floor surface and ease maintenance by reducing the adhesion of dirt and other debris.

STOPGAP 800 can also be pump applied.

COVERAGE

A 25kg bag of STOPGAP 800 mixed with 4.75 litres of clean water will cover approximately 3.0m² at a thickness of 5mm.

TECHNICAL INFORMATION

EN 13813 Class	CT-C40-F10-AR0.5	
Abrasion Resistance (EN 13892-4)	AR0.5	
Slip Resistance (without seal) (EN 13036-4)	Dry	72
	Wet	40
Working Time@ 20°C	20 - 30 minutes	
Walk on hardness time @ 20°C	90 minutes	
Time to traffic:	Foot traffic	3 hours
	Light traffic	24 hours
	Heavy traffic	3 days
Compressive Strength N/mm ² (EN 13892-2)	1 Day	>20.0
	7 Days	>30.0
	28 Days	>40.0
Flexural Strength N/mm ² (EN 13892-2)	1 Day	>4.0
	7 Days	>7.0
	28 Days	>10.0
Flow properties using 30mm ø x 50mm flow ring (EN 12706)	120 - 140 mm	
Consumption per mm thickness	1.69kg / m ²	
Application thickness:	5 - 15mm	



FEATURES

- Light to heavy-duty applications
- Excellent self-levelling properties
- Protein Free
- Application thickness from 5-15 mm
- Water mix
- Low odour
- Special class abrasion resistance

EN 13813:2002

The above standard refers to the properties and performance of the product and the specification to which it has been tested. The data shown confirms the minimum compressive strength, flexural strengths and abrasion resistance that the product will achieve.

PACKAGES

25 kg lined paper sacks.

HOW MUCH MATERIAL?

APPLIED THICKNESS	COVERAGE PER UNIT	CONSUMPTION PER 100m ² AREA
5mm	3.0m ²	34 units
10mm	1.5m ²	68 units
15mm	1.0m ²	102 units

N.B. Coverage rates are based on 4.75 litre water addition and will vary according to the condition of the subfloor.

SURFACE PREPARATION

Floor surfaces must be suitably prepared: sound, dry (<75%RH) and free from contaminants that may prevent adhesion. Use STYCCOCLEAN C140 for removing grease, oil, polish soap etc. from non-absorbent substrates. Concrete and sand/cement screeds must be fully cured and any laitance or surface treatments must be removed. The temperature of the floor must be maintained above 10°C throughout the application and drying of the compound. Underfloor heating must be off for at least 48 hours before, during and after application.

PRIMING - IT IS ESSENTIAL TO PRIME ALL SURFACES

Absorbent surfaces – Prime with a minimum 2 coats of dilute STOPGAP P131 to prevent uncontrolled rapid drying of the compound which may lead to surface pin holing, poor flow characteristics, surface imperfections and colour variation. Very absorbent surfaces may need additional coats of primer. If applying over STOPGAP 600, this should be done within 24 hours and the surface should first be primed with a dilute coat of primer followed by a neat coat.

Non-absorbent surfaces - such as terrazzo, quarry tiles and STOPGAP waterproof surface membranes should be primed with neat STOPGAP P131.

Apply the primer using a soft brush and do not extend the stated coverage. Site and substrate conditions vary, the chosen priming system should be evaluated over a trial area to ensure an optimum surface finish.

Alternatively, STOPGAP F77 may be used as a priming system in conjunction with a kiln dried grit 0.7-1.2mm:

Damp subfloors: Install STOPGAP F77 waterproof surface membrane as directed and within 24 hours apply a second coat of STOPGAP F77. Whilst still wet, fully blind the surface with the grit and allow to cure before vacuuming away all loose grit and installing STOPGAP 800.

Dry, absorbent subfloors: Apply one coat of STOPGAP F77 and whilst still wet, fully blind the surface with the grit and allow to cure before vacuuming away all loose grit and installing STOPGAP 800.

MIXING

Add 4.75 litres of clean water into a STOPGAP mixing bucket and gradually add all the powder whilst stirring with a power whisk fitted in an electric drill until a smooth creamy lump free consistency is achieved. The material should be mixed for a minimum of 2 minutes.

WATER ADDITION

4.5 litres minimum - 5.0 litres maximum per 25kg depending on consistency and flow properties required. Do not exceed 5.0 litres of water per 25kg bag.

PUMP APPLICATION

Mix in accordance with the pump manufacturer's recommendations and adjust the rate of water flow until the mix is a smooth fluid, uniform grey liquid with no surface separation. Flow checks should be carried out at regular intervals during pumping.

APPLICATION

Pour the mixed material onto the prepared subfloor and allow to flow and attain a smooth finish. Minimal work with a smoothing trowel is required. A spiked roller should be used immediately to eliminate entrapped air and smooth out flow lines to give a more uniform surface appearance. The mixed material should be applied at a thickness between 5mm to 15mm. For optimum smoothing and levelling characteristics, an overall thickness of at least 5mm should be maintained.

DRYING / OVERCOATING

Drying is dependent on the absorbency of the subfloor, ambient temperature and humidity. On both absorbent surfaces and non-absorbent surfaces, at a nominal 5mm thickness, the compound will be ready to receive STOPGAP SEAL after a minimum of 6 hours.

STOPGAP SEAL is designed to protect the surface from spillage of water or other fluids. Please refer to the STOPGAP SEAL data sheet. If required, the surface may be sealed with other epoxy coatings / paints for aesthetic reasons, greater slip resistance in the wet or to improve chemical resistance. Please consult Technical Service Department for specific products.

NOTE

When used as a finish in domestic or design feature installations, it should be noted that consistency of colour / finish cannot be guaranteed. This is down to the naturally sourced components used within STOPGAP 800 and variations in mixing and application methods. To minimise such colour variation, material should be selected from the same batch date of manufacture. Colour differences do not effect the overall high performance of this product. This product is not recommended for external use. We do not recommend applying subsequent layers of STOPGAP 800 as this can lead to surface pinholing / irregularities.

TOOLS

Suitable steel smoothing trowel, spiked roller, mixing bucket, electric drill and power whisk or suitable pumping equipment.

Wash tools with water immediately after use.

STORAGE

This product must be stored under cover, in unopened bags clear of the ground in cool dry conditions, protected from frost and excessive draught. Dampness will reduce the shelf life and may cause the powder to set in the sack.

SHELF LIFE

6 months in unopened bags and stored under good conditions.

HEALTH & SAFETY ADVICE

This product is not classified. Obtain the relevant Safety Data Sheet and follow the advice given. These can be found at www.f-ball.co.uk alternatively they can be obtained from the point of purchase or from F. Ball and Co. Ltd. at the address below.

Site conditions vary, to ensure this product is suitable and confirm this data sheet is current please contact Technical Service Department. For detailed information, request the F. Ball Subfloor Preparation Guide.

For further information about F. Ball products or more detailed technical assistance, please contact:



F. Ball and Co. Ltd.

Churnetside Business Park
Station Road, Cheddleton, Leek
Staffordshire ST13 7RS
United Kingdom

Tel: +44 (0) 1538 361633
Fax: +44 (0) 1538 361622
Tech Service Fax: +44 (0) 1538 361567
Email: mail@f-ball.co.uk

www.f-ball.co.uk

